



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: C09C 1/30, C08K 9/04	A1	(11) International Publication Number: WO 97/08250 (43) International Publication Date: 6 March 1997 (06.03.97)
(21) International Application Number: PCT/EP96/03246 (22) International Filing Date: 20 July 1996 (20.07.96) (30) Priority Data: 9517607.9 29 August 1995 (29.08.95) GB (71) Applicant (for all designated States except US): CROSFIELD LIMITED [GB/GB]; Bank Quay, Warrington WA5 1AB (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): ALDCROFT, Derek [GB/GB]; The Gables, 5 Wordsworth Way, Blueberries, Great Sutton, South Wirral L66 2YZ (GB). BATES, Sharron [GB/GB]; 4 Masefield Way, Ettiley Heath, Sandbach, Cheshire CW11 9ZJ (GB). EARL, Graham, James [GB/GB]; 21 Osprey Avenue, Moors Park, Winford, Cheshire CW7 1SE (GB). (74) Agent: HUGOT, Alain, E., P.; Unilever plc, Patent Division, Colworth House, Sharnbrook, Bedford MK44 1LQ (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.
(54) Title: SILICA PRODUCTS AND UV CURABLE SYSTEMS (57) Abstract Wax coated silica matting agent wherein the silica is an amorphous silica having a pore volume of at least 1.5 cm ³ /g, preferably at least 1.8 cm ³ /g, the wax coating being present in the range from 6 % to 15 % by weight of the matting agent and comprising a synthetic polyethylene wax.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

- 1 -

SILICA PRODUCTS and UV CURABLE SYSTEMSFIELD OF INVENTION

5 The invention relates to wax coated silica matting agents used in the matting of UV curable systems and to UV curable systems containing the same.

BACKGROUND TO THE INVENTION

10 UV curing is based on photoinitiated polymerisation of functional oligomers and monomers into a crosslinked polymer network. When an ultraviolet curable coating is exposed to UV energy in this way a relatively hard film, having an
15 extremely smooth surface, and hence one of high gloss, is produced. With the increasing popularity of radiation cured coatings for a wide variety of applications, the ability to control and reduce gloss is becoming more important. It is well known that matt surfaces provide the finished article
20 with a more elegant appearance and hide imperfections at the surface, particularly in wood, furniture and PVC flooring applications, and several different methods of reducing the gloss of UV curable coatings have been reported, for example the use of "dual cure" or "gradient intensity cure"
25 techniques, specific photoinitiators and non-silica type matting agents.

Traditional silica matting agents are conveniently used to reduce the gloss of solvent and water based finishes and in
30 the UV industry synthetic silicas are used to provide a semi-gloss or matt effect, although as a rule high concentrations are generally required by the formulator. The high solids nature of UV systems and the absence of adequate film shrinkage, required to ensure optimal levels
35 of particles are present in the surface of the cured film,

- 2 -

makes efficient matting difficult. Accordingly, high concentrations of conventional silicas are required to achieve an acceptable degree of gloss reduction. Such high levels of silica can frequently cause changes in the rheological properties of the lacquer which can be detrimental to the coating and curing process and, can impair the optical properties of the cured film.

In an attempt to overcome this problem, the use of large particle size silicas has been promoted in the past for both thin and thick film applications. Such materials may produce an unacceptable level of roughness particularly in thin coatings and, depending on the viscosity of the system, can result in a greater tendency to settle on prolonged storage. It would be desirable therefore to provide a synthetic silica matting agent for UV systems, having good efficiency and minimal effect on formulation viscosity and film properties.

There is therefore a need for a new matting agent which overcomes these problems.

Definitions and Test Procedures

i. Nitrogen surface area - pore volume

Nitrogen surface area is determined by standard nitrogen adsorption methods of Brunauer, Emmett and Teller (BET) using a multi point method with an ASAP 2400 apparatus supplied by Micromeritics of the U.S.A.. The samples are outgassed under vacuum at 270°C for at least one hour before measurement. Surface area is calculated from the volume of nitrogen gas adsorbed at p/p_0 0.98. This apparatus also provides the pore size distribution from which it is possible to get the pore

- 3 -

size (D_{10}) for which 10% of the pores are below this pore size. In the same manner, it is possible to get the pore size for which 50% (D_{50}) and 90% (D_{90}) of the pores are below this pore size. Additionally the pore volume (cm^3/g) for a given range of pore size can be obtained from the desorption curve.

ii. Matting efficiency in UV systems

In order to test the matting efficiency, two commercial UV curable systems have been chosen for the study, one is a urethane acrylate formulation (Formulation 2) and one is representative of an epoxy acrylate formulation (Formulation 1), details of which are given in the following Table.

Formulation 2	%	Formulation 1	%
Ebecryl 294	62.1	Ebecryl 608	44.7
N-vinyl pyrrolidone	9.5	OTA 480	22.2
2-ethyl hexyl acrylate	19.2	TPGDA	22.2
Benzophenone	2.85	Benzophenone	3.3
Darocur 1173	0.95	Irgacure 651	2.2
Silica matting agent	5.4	Silica matting agent	5.4

For the preparation of the formulations the following procedure was adopted. The binder and diluent were added to a 60ml amber glass jar and stirred at 8000rpm for 1 minute using an IKA Ultra Turrax T25 homogeniser.

- 4 -

The remaining additives and silica were then combined by hand stirring, followed by dispersion at 8000rpm for one minute. The systems were allowed to deaerate and then drawn onto black glass plates using either a 12 micron (Formulation 1) or a 40 micron bar applicator (Formulation 2). The plates were cured on a single pass, in line with normal industrial practice, under a Fusion H-bulb (mercury lamp, 120 W/cm) using a line speed of 3.5 metres/minute. The glossmeter readings at 60° (gloss) and 85° (sheen) were measured, by a BYK multiglossmeter.

iv. Weight mean particle size

The weight mean particle size is determined with the aid of a Malvern Mastersizer using 100mm path length lens. This instrument, made by Malvern Instruments, Worcestershire uses the principle of Fraunhofer diffraction utilising a low power He/Ne laser. Before measurement the sample was dispersed ultrasonically in water for a period of 7 minutes to form an aqueous suspension. The Malvern Mastersizer measures the weight particle size distribution of the silica. The weight mean particle size (d_{50}), the 10 percentile (d_{10}) and the 90 percentile (d_{90}) are easily obtained from the data generated by the instrument.

v. Wax content of the coated silica

The carbon content of the coated silicas is determined by a Leco HF 100 induction furnace and Leco CS 244 Carbon analyser. The carbon present is converted to carbon dioxide at high temperatures using the induction furnace. The gas is then detected by an infra-red

- 5 -

detection system. The wax content (in % w/w) is calculated from the carbon level obtained.

GENERAL DESCRIPTION OF THE INVENTION

5

It is a first object of the present invention to provide a wax coated silica matting agent characterised in that the silica is an amorphous silica having a pore volume of at least 1.5 cm³/g, preferably at least 1.8 cm³/g, the wax coating being present in the range from 6% to 15% by weight of the matting agent and comprising a synthetic polyethylene wax having a melting point of less than 85°C, preferably less than 80°C.

15 Preferably, the wax coating being is in the range from 10% to 15% by weight of the matting agent when the amorphous silica has a pore volume of less than 2.5 cm³/g.

20 It is a second object of the present invention to provide a UV curable system comprising 3 to 15% by weight of a matting agent wherein the mating agent is a wax coated silica, the silica being an amorphous silica having a pore volume of at least 1.5 cm³/g, preferably at least 1.8 cm³/g, the wax coating being present in the range from 6% to 15% by weight of the matting agent and comprising a synthetic polyethylene wax having a melting point of less than 85°C, preferably less than 80°C.

30 The wax coated silica matting agents are manufactured by a process that simultaneously melts the wax and comminutes the silica to the desired particle size distribution. Such a process is most effectively carried out in a fluid energy mill or microniser. The operating temperature can then be varied according to the requirements of the wax. The inlet temperature of the air being supplied to the fluid energy

35

- 6 -

mill must be high enough to ensure the wax melts within the residence time profile of the milling equipment.

SPECIFIC DESCRIPTION OF THE INVENTION

5

The present invention which will be further described in the following examples.

10

Various silicas were coated with different waxes using the following process.

15

Blends of silica feedstock and the appropriate wax (of particle size similar to that of the amorphous silica) were fed to an AFG 200 fluid bed mill (supplied by Alpine AG, Augsburg, Germany), operating at an air inlet temperature of 180°C., the classifier speed and feed rate being set commensurate with obtaining a micronised product with a weight mean particle size in desired range.

20

Amorphous coated silicas having the following characteristics were produced.

- 7 -

	PV (*) (cm ³ /g)	APS (**) (μm)	Coating	Wax content (%)
Ex. 1	1.2	8.4	None	
Ex. 2	1.2	8.8	Ternary blend (1)	10.0
Ex. 3	1.2	8.7	Microcrystalline (2)	11.4
Ex. 4	1.2	8.2	Polyethylene (3)	6.0
Ex. 5	1.2	8.1	Polyethylene (3)	11.4
Ex. 6	1.8	9.2	Microcrystalline	13.2
Ex. 7	1.8	7.2	Microcrystalline	8.7
Ex. 8	1.8	6.9	Ternary blend	14.8
Ex. 9	1.8	6.7	Polyethylene (3)	6.0
Ex. 10	1.8	7.2	Polyethylene (3)	11.6
Ex. 11	1.8	7.4	Polyethylene (4)	11.1
Ex. 12	1.8	8.0	Polyethylene (5)	12.9
Ex. 13	1.8	7.4	Polyethylene (6)	12.2
Ex. 14	1.8	7.3	Polyethylene (7)	10.4
Ex. 15	2.5	9.0	Polyethylene (3)	5.6
Ex. 16	2.5	8.3	Polyethylene (3)	13.4
Ex. 17	2.5	3.9	Polyethylene (3)	12.3
Ex. 18	2.5	7.7	Microcrystalline	8.1

(*) Pore volume of the uncoated amorphous silica

(**) Average Particle Size of the coated silica

- 8 -

- (1) as disclosed in EP-A-541,359
- (2) obtainable from Petrolite under the tradename Crown 700
- (3) obtainable from Petrolite under the tradename Polywax
400 (melting point 79.5°C)
- 5 (4) obtainable from Petrolite under the tradename Polywax
500 (melting point 88°C)
- (5) obtainable from Petrolite under the tradename Polywax
655 (melting point 99°C)
- 10 (6) obtainable from Petrolite under the tradename Polywax
1000 (melting point 113°C)
- (7) obtainable from Petrolite under the tradename Polywax
2000 (melting point 126°C)

15 Then the matting efficiency at 60° and 85° was measured for
the two formulations 1 & 2. The results are summarized in
the following table, a low number indicates a good matting
effect.

- 9 -

	Formulation 1		Formulation 2	
	60°	85°	60°	85°
Ex. 1	85	96	86	100
Ex. 2	82	90	85	96
Ex. 3	83	97	80	95
Ex. 4	91	95	81	94
Ex. 5	88	98	85	96
Ex. 6	88	90	84	90
Ex. 7	80	95	85	96
Ex. 8	88	90	78	95
Ex. 9	91	93	75	93
Ex. 10	54	93	9	32
Ex. 11	77	98	57	92
Ex. 12	89	101	75	90
Ex. 13	88	99	82	99
Ex. 14	88	96	83	97
Ex. 15	60	95	27	79
Ex. 16	57	98	13	55
Ex. 17	71	98	20	76
Ex. 18	91	92	83	90

As it can be seen, only examples 10, 15, 16 and 17 present good matting properties.

From examples 1 to 5, it can be seen that irrespective of the coating which is used, no satisfactory matting

- 10 -

properties are obtained. Examples 1 to 5 are characterized by a pore volume of 1.2 cm³/g.

5 In examples 6 to 14 (pore volume of 1.8 cm³/g), only example 10 gives satisfactory matting properties whereas the only difference between example 10 and example 9 is the wax content of the silica, proving at a pore volume of 1.8 cm³/g, a wax content of 6% is not enough to give the desired matting properties.

10

In examples 10 to 14 (various polyethylene wax types), only example 10 gives satisfactory matting performance, proving that the type of polyethylene wax, as defined by its melting point, is critical.

15

In examples 15 to 18 (pore volume of 2.5 cm³/g), examples 15 to 17 gives satisfactory matting properties, even at low loading (example 15), whereas example 18, even though at 8.1% loading does not give the required properties.

- 11 -

CLAIMS

1. Wax coated silica matting agent characterised in that the silica is an amorphous silica having a pore volume of at least 1.5 cm³/g, preferably at least 1.8 cm³/g, the wax coating being present in the range from 6% to 15% by weight of the matting agent and comprising a synthetic polyethylene wax.
2. Wax coated silica according to claim 1 wherein the amorphous silica has a pore volume of less than 2.5 cm³/g, the wax coating being present in the range from 10% to 15% by weight of the matting agent.
3. Wax coated silica according to claim 1 or 2 wherein the amorphous silica has a matting efficiency of below 20 gloss units at an incidence angle of 60° and a loading of 5.4% by weight in the urethane acrylate formulation (2).
4. Wax coated silica according to claim 1 wherein the synthetic polyethylene wax has a melting point of less than 115°C, preferably less than 100°C, more preferably less than 85°C.
5. UV curable system comprising 3 to 15 % by weight of a matting agent wherein the matting agent is a wax coated silica, the silica being an amorphous silica having a pore volume of at least 1.5 cm³/g, preferably at least 1.8 cm³/g, the wax coating being present in the range from 6% to 15% by weight of the matting agent and comprising a synthetic polyethylene wax having a melting point of less than 85°C, preferably less than 80°C.

INTERNATIONAL SEARCH REPORT

Interns | Application No
PCT/EP 96/03246

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09C1/30 C08K9/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08K C09C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 541 359 (CROSFIELD JOSEPH & SONS) 12 May 1993 see page 3, line 6 - line 8 see claims 1-3	1-5

A	US,A,4 097 302 (COHEN HOWARD JOSEPH ET AL) 27 June 1978 see claims 1-3	1-5

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

14 October 1996

Date of mailing of the international search report

25.10.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern: J Application No
PCT/EP 96/03246

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0541359	12-05-93	AT-T- 125283	15-08-95
		CA-A- 2082035	08-05-93
		DE-D- 69203570	24-08-95
		DE-T- 69203570	01-02-96
		US-A- 5326395	05-07-94

US-A-4097302	27-06-78	NONE	
